

Technical Data Sheet



Eclectic Products LLC
Manufacturing Facility
101 Dixie Mae Drive
Pineville, Louisiana
eclecticproducts.com
800.349.4667

ISO 9001:2008
Compliant
Quality Management
Systems

Administration Office
Eugene, Oregon
eclecticproducts.com
800.693.4667

UNITED STATES



0.18 fl oz (Clear)

1.0 fl oz (Clear)

3.7 fl oz (Clear & Black)

Not all styles/sizes/colors available in all areas

AUSTRALIA/NZ



5.1 G (Clear)

28.5 G (Clear)

105.6 G (Clear & Black)

Not all styles/sizes/colors available in all areas

SHOE GOO

SHOE REPAIR ADHESIVE



PRODUCT DESCRIPTION

SHOE GOO has been scientifically formulated to repair, seal and stick to a wide variety of materials with superior strength to any other brand. SHOE GOO contains a resin system designed for stronger abrasion resistance and better adhesion to flexible materials. Leather, rubber, vinyl and canvas – SHOE GOO is the most versatile and effective adhesive available.

WHERE TO USE / APPLICATIONS

- Rebuild your worn-out soles overnight
- Seal rubber boots, galoshes and waders
- Coat & protect shoes to avoid premature wear
- Repair damages heels; secure loose insoles
- Reinforce and protect skate shoes; coat skateboards for extra traction

FEATURES AND BENEFITS

WATERPROOFING – water resistant immediately upon application

REPAIRING WORN SOLES – makes your favorite footwear last longer

FISHING/FOUL WEATHER GEAR – repair on the reinforced fabric inside

TECHNICAL INFORMATION

| PROPERTIES | |
|------------------------|---|
| UNCURED MATERIAL | |
| Color: | Clear and Black |
| VOC: | 466 grams/liter |
| Solvent: | Toluene, Petroleum Distillates (flammable) |
| Density: | 7.5 lbs/gal |
| Solids: | 46% by weight, 42% by volume |
| Viscosity: | 170,000 cps |
| Tack time: | 2 to 3 minutes |
| Set time: | 20 minutes* |
| Full cure time: | Thin film: 24 hours / Thick film: 48 to 72 hours |
| Storage: | Ideal temperature range: 50 to 80 °F (10 and 27 °C). Product may thicken when stored in colder temperatures but will not freeze. If product thickens from colder temperatures, warm to room temperature before use. |
| Freeze/thaw stability: | Stable, allow product to warm to room temperature before using |
| Shelf life: | 2 years (unopened) |

**Depending on material, humidity and temperature.*

| CURED MATERIAL | |
|----------------------|---|
| Chemical resistance: | Excellent to water, dilute bases |
| UV resistance: | None; paint-over for UV resistance |
| Hardness: | 80 Shore A |
| Dielectric strength: | 400V/mil (ASTM D-149); this is the maximum voltage that can be applied to a given material without causing it to break down |
| Tensile strength: | 3800 lb/in ² (ASTM D-412) |
| Elongation: | 900% (ASTM D-412) |
| Service temperature: | -40 to 150 °F (-40 to 66 °C) |
| Paint-over time: | 24 hours |

SHOE GOO

SHOE REPAIR ADHESIVE

CHEMICALS THAT HAVE LITTLE OR NO EFFECT ON SHOE GOO

| | |
|--|--|
| Acetic acid (5% and 10%) Ammonium hydroxide (3.4%) Ammonium nitrate (50%) Antifreeze Beer (3.2% alcohol by volume) Boric acid (3.1%) Distilled water Hydraulic oil Lactic acid (3.8%) Milk (fresh, tested at 40 °F) Motor oil (30w) Nitric acid (10% and 20%) Oxalic acid (3.1%) Phosphoric acid (30% and 60% as P ₂ O ₅) Potassium hydroxide (3.4%) Sodium carbonates (2.7%) Sodium chloride (10%) Sulfuric acid (3% and 10%) Wine (20% alcohol by volume) | SHOE GOO exhibits excellent resistance to water, dilute acids and dilute bases. Thin films of SHOE GOO were immersed in various chemicals for two weeks and exhibited weight gains of less than 2% and tensile strength loss of less than 10%. These chemicals are listed on the left. All percentages are given by weight unless otherwise noted. |
|--|--|

SOLVENTS THAT DISSOLVE SHOE GOO

| | |
|--|--|
| Chevron solvent 1100 Chlorothane NU Cyclohexane Gasoline Methylene chloride Perchloroethylene Propyl acetate Toluene 1, 1, 1-Trichloroethane | These are common solvents that dissolve SHOE GOO when hardened samples were immersed. The dissolution with these solvents was not instantaneous and therefore does not preclude usage in all cases. Applications were an occasional splash or brief exposure is expected may be acceptable. Test a small area before full use. |
|--|--|

DIRECTIONS and APPLICATION NOTES

Read directions and test small area before use.

- Step 1 Surface should be clean, dry and free of dirt.
- Step 2 Puncture seal in neck of tube using pointer cap. Ideal application temperature range is 50 to 90 °F (10 to 32 °C). However, fully cured adhesive can withstand temperatures from -40 to 180 °F (-40 to 82 °C) intermittently.
- Step 3 Apply directly to surfaces to be protected, bonded or repaired. For waterproofing and protecting, use thin coats (spread with a disposable tool) to build a thick coating, allowing each layer to set 3-4 hours.
- Step 4 Allow repair to cure for 24 hours. Depending on the materials and temperature, maximum strength may not be reached for 48 to 72 hours.
- Step 5 For future easy cap removal, apply a thin coat of petroleum jelly to the threads of the tube before replacing the cap.
- Step 6 Clean uncured adhesive with acetone or citrus-based solvents. Cured material may be removed by cutting or scraping.

- Please read all directions before using. Use in well-ventilated area.
- May damage finished surfaces. Avoid such contact until completely dry. Not recommended for use on polystyrene, polyethylene, polypropylene, Styrofoam™ or paper products, and any items that come into contact with food, drinking water or animals.
- Ice can be used when applying as a coating for ease of spreading across surface.
- For repairing and protecting Skate shoes, visit: shoegooskate.com



SHOE GOO

SHOE REPAIR ADHESIVE

HEALTH and SAFETY

This product contains toluene and petroleum distillate. Before working with this product, read and become familiar with information concerning hazards, proper use and handling. SDS's are available online at the following links:

USA-

English (Clear): <http://eclecticproducts.com/downloads/sds-shoegoo-clear-english.pdf>

Spanish (Clear): <http://eclecticproducts.com/downloads/sds-shoegoo-clear-spanish.pdf>

English (Black): <http://eclecticproducts.com/downloads/sds-shoegoo-black-english.pdf>

Spanish (Black): <http://eclecticproducts.com/downloads/sds-shoegoo-black-spanish.pdf>

Australia/New Zealand-

English (Request SDS): sds@eclecticproducts.com

To request a hard copy of the SDS, please send an e-mail to sds@eclecticproducts.com.

⚠WARNING: This product can expose you to chemicals including toluene and carbon black which are known to the State of California to cause cancer and birth defects or other reproductive harm. For more information go to www.p65warnings.ca.gov.

LIMITED WARRANTY

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable state law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products, Inc., P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. This warranty gives you specific legal rights, and you also have other rights, which vary from state to state.

