

TECHNICAL DATA SHEET

OLD MASTERS® BRUSHING LACQUER

AVAILABLE SIZES: Spray (10), Quart (04) and Gallon (01)

PRODUCT CODES: 927 Gloss
928 Semi-Gloss
929 Satin

PRODUCT DESCRIPTION: Old Masters® Brushing Lacquer is a crystal clear, fast drying and self-leveling interior lacquer for use on wood, fiberglass and primed metal surfaces. It provides a durable finish, resistant to water and alcohol. It is easily repaired and recoated without removing the old finish. Fast drying, this formula allows multiple coats and one-day finishing. This is a nitrocellulose lacquer.

SURFACE PREPARATION: All surfaces must be clean, dry and free from dirt, wax, grease, glue and other contaminants or penetration and adhesion will be affected.

Bare Wood: Sand surface thoroughly with medium grit sandpaper and progress to fine grit sandpaper. Always sand in the direction of the wood grain. Remove dust with tack rag.

Previously Finished Surfaces: Surface should be sanded to remove imperfections and gloss, using extra fine sandpaper (220 grit), sanding with the grain. Remove dust with a tack rag. Before applying Brushing Lacquer to previously finished surfaces, test on an inconspicuous area. If wrinkling or lifting of the old finish occurs, remove with a wax-free paint remover and refinish as a bare wood surface.

Stained Surfaces: Stain must be thoroughly dry before applying clear finish. Do not sand uncoated stained surfaces.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION: Stir thoroughly before and during application. DO NOT SHAKE. For larger projects requiring more than one container, combine containers and mix to ensure gloss uniformity. Test the finish on an inconspicuous area to ensure adequate adhesion. Do not apply in direct sunlight or areas of extreme air movement.

1. Apply with brush, flat pad or spray.
2. Flow on generously with minimum brushing to achieve a glass-like finish. Maintain a wet brush, applying with the grain.
3. Brushing Lacquer will dry to touch in 30 minutes. Sanding is not required between coats unless surface feels rough. If necessary, sand with very fine sandpaper and remove dust. Allow 2 hours between coats.
4. Reapply. A minimum of three coats is recommended for ultimate protection. In high moisture areas, apply up to 6 coats to prevent white water spotting. Allow finish to cure for at least 24 hours before subjecting to normal use.

TECHNICAL DATA SHEET

OLD MASTERS® BRUSHING LACQUER

THINNING: Do not thin. Use as packaged.

COVERAGE: Approximately 200 to 300 square feet per gallon. Coverage will vary significantly depending on application method and condition of wood.

DRYING TIME: Apply when air and surface temperatures are between 60° and 90°F and humidity is between 30% and 70%. At 50% relative humidity and 70°F, Brushing Lacquer will dry to touch in 30 minutes. Recoat after 2 hours. Dry time will be affected by temperature, humidity and film thickness. Protect product from freezing prior to and during application.

Wait 24 hours before subjecting surfaces to light use. Care should be used during the first week after application as the finish is curing to its ultimate hardness.

CLEAN UP: Lacquer thinner is recommended for cleanup. The use of lacquer thinner may violate VOC compliance in your area. Check with your local government agencies to ensure proper compliance.

To avoid spontaneous combustion during temporary storage, soak soiled rags and waste immediately after use in a water-filled, closed metal container.

MAX VOC: 680 grams/liter (5.7 lbs/gal)

TECHNICAL DATA

GLOSS:	@ 60° Gloss 90+ Semi-Gloss 55 to 65 Satin 25 to 35	WEIGHT PER GALLON:	7.76-7.80 lbs
	27 to 28%	FLASH POINT:	66°F
SOLIDS BY VOLUME:	18 to 19%	VISCOSITY AT 77 °:	Gloss 20-25 sec. #2 Zahn Cup Semi-Gloss 20-25 sec. #2 Zahn Cup Satin 26-30 sec. #2 Zahn Cup
	680 grams/liter	AVERAGE DRY TIME @ 70°F AND 50% R.H.:	Approximately 30 minutes. Recoat after 2 hours
THEORETICAL COVERAGE @ Mil DFT:	300 sq. ft. per gal.	VEHICLE:	Lacquer
COVERAGE @ RECOMMENDED DFT	150 to 300 sq. ft. per gal.	RECOMMENDED THINNER:	Do not thin. Used as packaged.
RECOMMENDED DFT PER COAT:	1 to 2 Mils DFT		

Limited Warranty Since Old Masters® does not control the application of its products, nor is the condition of the surface to which they are applied, a Limited Warranty provided. If the products do not perform as specified, for whatever reason, Old Masters® liability will under no circumstances exceed the replacement of the product.