



**AMERICAN ACCENTS  
DESIGNER METALLIC SPRAYS**

**DESCRIPTION AND USES**

Rust-Oleum® American Accents® Designer Metallic Sprays provide a durable protective coating that resists chipping and peeling with no metallic rub off.

**PRODUCTS**

SKU (12 ounces)	Description
202642	Classic Bronze
202646	Aged Bronze
202719	Aged Brass
243896	Satin Nickel

**PRODUCT APPLICATION**

**PAINTING CONDITIONS**

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

**SURFACE PREPARATION**

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile.

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**PRODUCT APPLICATION**

**PRIMING**

Use of Rust-Oleum American Accents 7980 Aerosol Primer promotes adhesion and enhances hiding and is especially recommended for bare wood and metal. Apply an undercoat of primer on darker surfaces to maximize finish coat color.

**APPLICATION**

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 1 light coat followed by 1 wet coat for the best appearance. A wet coat should appear shiny as it is applied to the surface. **Do not use near open flame.**

**DRY & RECOAT**

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 10 minutes and is fully dry in 30 minutes. Wait at least 4 hours before applying finish over the 7980 Primer.

**CLEAN-UP**

When finished spraying, clear spray by turning can upside down and depressing spray button for 3-5 seconds (some paint will be sprayed out, so be careful to not inadvertently spray yourself or other objects). Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

**CLOGGING**

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

**TECHNICAL DATA**

**AMERICAN ACCENTS DESIGNER METALLIC SPRAYS**

**PHYSICAL PROPERTIES**

		DESIGNER METALLIC SPRAYS
<b>Resin Type</b>		Solvent Acrylic
<b>Pigment Type</b>		Varies with color
<b>MIR</b>		Maximum value of 1.25
<b>Fill Weight</b>		12 ounces
<b>Solvents</b>		Acetone, Toluene, Xylene
<b>Recommended Dry Film Thickness (DFT) per Coat</b>		1.0-2.0 mils (25-50μ)
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		10-12 sq.ft./can (0.9-1.09 m <sup>2</sup> /can)
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Touch</b>	15 minutes
	<b>Handle</b>	30 minutes
	<b>Recoat</b>	Wait at least 4 hours after applying 7980 Primer
<b>Shelf Life</b>		5 years
<b>Flash Point</b>		-156°F (-104°C)
<b>Safety Information</b>		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.