



**CHALKED
DECORATIVE GLAZE**

DESCRIPTION AND USES

Rust-Oleum® Chalked Decorative Glaze allows you to add a custom antiqued finish to any Chalked painted surface. This semi-transparent Decorative Glaze has good workability, allowing you to customize a handcrafted final look. Chalked Decorative Glaze enhances the details of brush strokes, wood grain, corners, crevices and more. Ideal for Chalked painted surfaces on wood, laminate, melamine or metal surfaces.

For interior use only.

PRODUCTS

SKU	DESCRIPTION
315881	Aged Glaze
315883	Smoked Glaze

PAINTING CONDITIONS

Apply when temperature is between 50-95°F (10-35°C) and humidity is below 70% to ensure proper drying.

PRODUCT APPLICATION

IMPORTANT! The Chalked Decorative Glaze must be applied over a clean, fully cured surface that has been painted with Rust-Oleum Chalked Paint. The Chalked Paint is fully cured in 3-4 days.

To promote a high-end finish look, a cloth such as cheesecloth or a lint-free rag should be used to remove portions of the Chalked Decorative Glaze. Be sure to test glazing in a small area first before applying on the entire project.

PRODUCT APPLICATION (cont.)

APPLICATION

Stir thoroughly. Do not shake the can. Thinning is not required.

Using a 2" synthetic brush or a 2" foam brush, coat the surface with the Chalked Decorative Glaze. Be certain to apply the Decorative Glaze in all corners, crevices and raised panel sections. Using cheesecloth, wipe the surface (using varying pressure) to remove the Chalked Decorative Glaze to a desired look. If not satisfied with the appearance of the Decorative Glaze, while wet, lightly wipe the surface with a clean damp cloth and repeat the glazing process. On wood surfaces, wipe off in the direction of the wood grain.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Let dry a minimum of 8 hours before applying Rust-Oleum Chalked Matte Clear Protective Topcoat. The Clear coat is optional, but highly suggested for optimal service life.

COVERAGE

Each quart covers 150-200 square feet.

CLEAN-UP

Clean brush and other and application tools with soap and water.

**TECHNICAL DATA****CHALKED DECORATIVE GLAZE****PHYSICAL PROPERTIES**

		CHALKED DECORATIVE GLAZE
Resin Type		Acrylic
Pigment Type		Varies depending on color
Solvents		Water and Propylene Glycol
Weight	Per Gallon	8.6-8.7 lbs.
	Per Liter	1.03-1.04 kg
Volatile Organic Compounds		<860 g/l (7.15 lbs./gal.)
Wet Film to Achieve DFT		Varies depending on surface type and porosity
Practical Coverage at Recommended DFT		150-200 sq.ft./qt. (13.9-18.6 m ² /quart)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Recoat with Clear	8 hours
Shelf Life		3 years
Flash Point		>200°F (93°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061
An RPM Company

Phone: 877-385-8155
www.rustoleum.com

Form: GDH-1280
Rev.: 011518