



**BULLS-EYE 1-2-3®
GRAY PRIMER FOR ALL SURFACES**

DESCRIPTION AND USES

Zinsser® Bulls-Eye 1-2-3® Gray Primer is an all purpose, high performance, water-based primer for interior and exterior residential, commercial and industrial applications. Bulls-Eye 1-2-3 Gray Primer has excellent stain blocking resistance, is fast dry, and has excellent adhesion to glossy surfaces. Use Bulls-Eye 1-2-3 Gray Primer with rich or dark topcoat colors to improve their hide and coverage. May be used under and over any oil or latex architectural paint. The dried film is mold and mildew resistant.

PERFORMANCE CHARACTERISTICS

- Sticks to all surfaces without sanding
- Seals uniformly
- Blocks stains
- Use with any topcoat
- Dries in 1 hour

PRODUCTS

SKU	Description
290971	13 oz. Aerosol (Gray)
285085	1-Gallon (Gray)
285090	5-Gallon (Gray)
286258	1-Quart (Gray)

PRODUCT APPLICATION

SURFACE PREPARATION

Surfaces should be clean, dry, sound and free of any contamination, mildew, rust or unsound coatings that may interfere with adhesion. If unsure of cleanliness, always wash surface with an appropriate cleaner or solvent. **DO NOT** use TSP as a cleaner. Remove any peeling and/or unsound coatings. Scuff sand bare aluminum. Sand any remaining paint film edges smooth. Spot prime knots and sap streaks with Zinsser B-I-N Primer Sealer.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-Approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

PRIMING

Use Bulls-Eye 1-2-3 Gray Primer on all types of bare or painted surfaces including wood, drywall, cured plaster, concrete, stucco and masonry, aluminum, vinyl, steel, galvanized metal and PVC. It has excellent adhesion to dense glossy surfaces such as enamel paints and varnishes, paneling, laminates and ceramic tile without sanding or de-glossing. It also hides dark surfaces.

SEALING

Bulls-Eye 1-2-3 Gray Primer seals porous surfaces and provides a smooth and even finish to extend the coverage of topcoats and provide uniform and consistent sheen. It helps bind chalky surfaces and is suitable for use on moderately chalked aluminum or previously painted siding and trim.

STAIN BLOCKING

Bulls-Eye 1-2-3 Gray Primer blocks stains from grease, handprints, asphalt, crayon, graffiti, rust stains, light water stains and cedar or redwood bleed. Note: When priming over bare cedar or redwood, allow 24 hours dry time before painting. Certain applications may require a second coat of primer. Prime severe water and smoke stains and block associated odors with Zinsser B-I-N Ultimate Stain-Blocker.

MIXING

Brush Goods - Mix thoroughly to ensure any settled pigment is re-dispersed. DO NOT THIN.

APPLICATION

Apply only when air, material, and surface temperatures are between 50-90°F (10-32°C) and the relative humidity is below 85%.

Brush Goods - Thoroughly mix to ensure any settled pigment is re-dispersed before using. Apply using a synthetic (nylon or polyester) bristle brush, roller, or airless sprayer. Follow manufacturer's instructions when using spray equipment. For airless spraying use a 0.017" tip at 2000 to 2500 psi. Wear NIOSH approved respirator and provide adequate ventilation.

Aerosol – **Do not spray indoors.** Shake can vigorously for one minute after the mixing ball begins to rattle. Turn upside down and continue shaking for one minute. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-12" from surface and spray with short 'dusting' strokes', slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**



TECHNICAL DATA

BULLS-EYE 1-2-3® GRAY PRIMER FOR ALL SURFACES

PRODUCT APPLICATION (cont.)

THINNING

Brush Goods - If thinning is necessary, add no more than 10 fluid ounces of clean water per gallon and mix thoroughly. Apply a second coat of primer full body. Note that thinning the primer may affect its stain-blocking properties.

TINTING

Bulls-Eye 1-2-3 Gray Primer may be tinted to improve hide and coverage with darker and deeper colors. It can be tinted with up to 4 ounces (118 ml) of universal colorant per gallon. Tinting may increase dry and cure times. Shake or stir well before using.

COVERAGE

Bulls-Eye 1-2-3 Gray Primer will cover approximately 400-450 square feet per gallon. Coverage may vary with application method and surface porosity.

DRY TIME

Brush - Dries to the touch in 30 minutes, can be recoated in 1 hour. Aerosol - Dries to the touch in 30 minutes, can be recoated in 30 minutes. Full adhesion and hardness develops in 7 days. Lower temperatures, higher humidity, and the addition of tint will prolong dry and cure time. Allow more time at cooler temperatures.

PRODUCT APPLICATION (cont.)

CLEAN-UP

Brush Goods - Clean up spills and paint drips with warm water and liquid detergent. Wipe up splatters before they dry. Follow manufacturer's directions to clean spray equipment. Dispose of unused or unwanted product in accordance with local laws regulating water-based coatings.

Aerosol - Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor. If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

LIMITATIONS

Not recommended for application to floors or decks or to surfaces subject to immersion or prolonged contact with water.

**TECHNICAL DATA****BULLS-EYE 1-2-3® GRAY PRIMER FOR ALL SURFACES****PHYSICAL PROPERTIES**

Physical Properties		AEROSOL	BULLS-EYE 1-2-3 GRAY PRIMER
Resin Type		Acrylic Modified Alkyd	Styrene Acrylic Copolymer
Pigment Type		Titanium Dioxide, Calcium Carbonate, Talc	Titanium Dioxide, Calcium Carbonate, Talc
Solvents		Acetone, Aliphatic Hydrocarbons	Water, Glycol Ethers
MIR		0.70 Max	NA
Fill Weight		13 ounces	NA
Weight	Per Gallon	NA	10.7 lbs.
	Per Liter	NA	1.3 kg
Solids	By Weight	NA	51.7%
	By Volume	NA	38.1%
Volatile Organic Compounds		NA	<100 g/l (0.83 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		1.5-2.5 mils (37.5-62.5µ)	1.0-1.5 mils (25-37.5µ)
Wet Film to Achieve DFT (Unthinned material)		NA	2.5-4.0 mils (62.5-100µ)
Practical Coverage at Recommended DFT (assume 15% material loss)		10-12 sq.ft./can (0.9-1.1 m ² /can)	Approximately 400-450 sq.ft./gal. depending on application method and surface porosity
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	30 minutes	30 minutes
	Recoat	30 minutes	1 hour
	Full Hardness	7 days	7 days
Shelf Life		5 years	5 years
Flash Point		-156°F (-104°C)	>200°F (93°C)
Storage		NA	40-90°F (4-32°C)
Safety Information		For additional information, see SDS	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.